

Corundum mullite push plate



Project	Corundum mullite push plate
Al ₂ O ₃	≥80%
Sic	—
SiO ₂	≤18
Fe ₂ O ₃	≤0.3%
Bulk density g/cm ³	≥2.7
Apparent porosity	≤22%
Pressure strength at normal temperature MPa	≥80
Thermal shock stability (1100°C Water Cooling)	≥30
Maximum Using Temperature	1650°C
Appearance Dimension Of Push Plate	340*340*30
Order Quantity	100 Pieces
Manufacture period	30-45 Days